

4332 Ti

CATEGORY SMAW Stick Electrodes

TYPE Rutile basic electrode for welding stainless steels and dissimilar steels.

APPLICATIONS Joining heat resistant CrNi-steels of the same kind and also joining dissimilar metals such as steel to stainless steel. Cladding on low alloyed steels in case a 18/8 CrNi layer is required in the first layer. Scale resistant up to 1050°C.

PROPERTIES High corrosion resistance and excellent weldability on both AC and DC+. The weld deposit can undergo a high polish due to the low carbon content.

CLASSIFICATION

AWS	A 5.4: E 309L-26
EN ISO	EN 1600: E 23 12 LR 32
DIN: W.Nr.	1.4332
DIN	8556: E 23 12 LR(B) 23

SUITABLE FOR W.Nrs: 1.4541, 1.4550, 1.4710, 1.4712, 1.4727, 1.4729, 1.4740, 1.4742, 1.4780, 1.4825, 1.4826, 1.4828, 1.4878

APPROVALS CE approved

WELDING POSITIONS:



WELD DEPOSIT WEIGHT %

C	Mn	Cr	Ni	Mo	Fe
<003	0.5-2.0	21-23	11-13	-	Rem

MECHANICAL PROPERTIES

Heat Treatment	R _{p0,2} (N/mm ²)	R _m (N/mm ²)	A ₅ (%)	Impact Energy (J) ISO-V			Hardness HRc / HV
				20°C	-40°C	-60°C	
AW	400	550	30	55			

AW: as welded

WELDING PARAMETERS / PACKING

Welding Parameters			Packing		
D (mm)	Length (mm)	Current (A) DC+/AC	kg / can	kg / 6pack	kg / 1000
2,0	300	40-60	2.4	14.4	-
2,5	300	60-90	2.4	14.4	18.4
3.2	350	80-110	2.8	16.8	35.4
4.0	350	100-150	2.8	16.8	53.9
5.0	450	150-200	3.2	19.2	108.8

REDRYING TEMPERATURE 300°C/2hr