

4842 Kb

CATEGORY SMAW Stick Electrodes

TYPE Basic coated electrode for heat resistant stainless steels

APPLICATIONS Common applications include industrial furnaces, annealing chambers, fused salt treatment installations and boiler parts, as well as heat exchangers..

PROPERTIES For welding heat-resistant austenitic steels of the 25% Cr, 20% Ni types. 4842 Kb has good general oxidation resistance, especially at high temperatures, due to its high Cr content. The alloy is fully austenitic and is therefore sensitive to hot cracking. The temperature limits for use under intermittent oxidation depend on cycle frequency. In no case shall a temperature of 1000°C be exceeded. This alloy can withstand relatively severe thermic shock, and is superior to type 309 L.

CLASSIFICATION

AWS	A 5.4: E 310-15
EN ISO	3581-A: E 25 20 B 22
DIN: W.Nr.	1.4842
DIN	8556: E 25 20 R 26

SUITABLE FOR 1.4823, 1.4826, 1.4828, 1.4832, 1.4840, 1.4841, 1.4846, 1.4848, 1.4837, 1.4710, 1.4713, 1.4724, 1.4726, 1.4742, 1.4745, 1.4762, 1.4845, 1.4849 heat resistant stainless steel, AISI 305, 310, 314, ASTM A297 HF, A297 HJ

APPROVALS CE approved

WELDING POSITIONS:



WELD DEPOSIT WEIGHT %

C	Mn	Si	Cr	Ni	Fe
<0.1	2.5-3.0	0.6	23-26	19-21	Rem

MECHANICAL PROPERTIES

Heat Treatment	R _{p0,2} (N/mm ²)	R _m (N/mm ²)	A ₅ (%)	Impact Energy (J) ISO-V			Hardness HV 40
				20°C	-40°C	-196°C	
AW	>410	>600	>29	>70		>32	200

AW: as welded

WELDING PARAMETERS / PACKING

Welding Parameters			Packing		
D (mm)	Length (mm)	Current (A) DC+/ \bar{A} C	kg / can	kg / 6pack	kg / 1000
2.5	300	80-110	2.5	15	
3.2	350	100-150	2.8	16.8	
4.0	350	150-190	3.0	18	
5.0	350	160-210			

REDRYING TEMPERATURE 320°C/2hr (not often required).