

SA 307

CATEGORY	SAW Submerged arc
----------	-------------------

CLASSIFICATION	AWS	A 5.9: ER 307
	EN ISO	14343-A: S 18 8 6
	DIN: W.Nr.	1.4370

SUITABLE FOR	Buffer layers before hardfacing, armor plate, (type 409, 304), high Manganese austenitic steel, heterogeneous welding, difficult to weld steels such as: 42CrMo4, C45, 42MnV7, tool steels etc.
--------------	---
