


## AlMg 5

<b>CATEGORY</b>	GMAW-GTAW Solid wires																																					
<b>TYPE</b>	Mig filler metal for welding Aluminium Magnesium alloys.																																					
<b>APPLICATIONS</b>	Filler metal for welding Aluminium alloys with maximum 5% Magnesium. This Magnesium alloyed Aluminium wire, thanks to its excellent corrosion resistance and its high mechanical properties is mainly used in ship yards, car and railway industry. Thicker sections should be preheated (150°C) prior to welding.																																					
<b>PROPERTIES</b>	Excellent weldability and good mechanical strength combined with good corrosion resistance are typical for this alloy. The weld deposit is free from porosity due to the special shaving process and cleaning method during production. AlMg5 is one of the most popular types within the range of aluminum alloys and covers a weight range of alloys.																																					
<b>CLASSIFICATION</b>	AWS	A 5.10: ER 5356																																				
	EN ISO	18273: S Al5356-AlMg5Cr A																																				
	DIN: W.Nr.	3.3556																																				
	DIN	1732: SG-AlMg5																																				
<b>SUITABLE FOR</b>	Aluminium alloys: AlMg3, AlMg4, AlMg5, AlMgMn, AlZnMg1, G-AlMg3Si, G-AlMg5Si, G-AlMg10, AlMg1SiCu, AlMgSi0,7, AlZn4,5Mg1, AlSi1MgMn, AlSiMg(A), 3.3545, 3.3206, 3.3210, 3.2315, 3.3211, 3.4335, EN AW 5086, EN AW 6060, EN AW 6005A, EN AW , EN AW 6061, EN AW 7020, EN AC 51400, EN AC 51300, EN AC 51100, EN AW 5454																																					
<b>APPROVALS</b>	CE approved																																					
<b>WELDING POSITIONS:</b>																																						
<b>CHEMICAL COMPOSITION %</b>	<table border="1"> <thead> <tr> <th>Be</th> <th>Mn</th> <th>Si</th> <th>Cr</th> <th>Fe</th> <th>Cu</th> <th>Al</th> <th>Mg</th> <th>Zn</th> <th>Ti</th> <th>other</th> </tr> </thead> <tbody> <tr> <td>0.0008</td> <td>0.05-2</td> <td>0.2</td> <td>0.05-0.2</td> <td>0.4</td> <td>0.1</td> <td>rest</td> <td>4.5-5.5</td> <td>0.1</td> <td>0.06-0.12</td> <td>0.15</td> </tr> </tbody> </table>		Be	Mn	Si	Cr	Fe	Cu	Al	Mg	Zn	Ti	other	0.0008	0.05-2	0.2	0.05-0.2	0.4	0.1	rest	4.5-5.5	0.1	0.06-0.12	0.15														
Be	Mn	Si	Cr	Fe	Cu	Al	Mg	Zn	Ti	other																												
0.0008	0.05-2	0.2	0.05-0.2	0.4	0.1	rest	4.5-5.5	0.1	0.06-0.12	0.15																												
<b>MECHANICAL PROPERTIES</b>	<table border="1"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R<sub>p0,2</sub> (N/mm<sup>2</sup>)</th> <th rowspan="2">R<sub>m</sub> (N/mm<sup>2</sup>)</th> <th rowspan="2">A<sub>5</sub> (%)</th> <th colspan="3">Impact Energy (J) ISO-V</th> <th rowspan="2">T (°C)</th> </tr> <tr> <th>-20°C</th> <th>-40°C</th> <th>-60°C</th> </tr> </thead> <tbody> <tr> <td>AW</td> <td>115-140</td> <td>275-315</td> <td>25-35</td> <td></td> <td></td> <td></td> <td>562-633</td> </tr> </tbody> </table>		Heat Treatment	R <sub>p0,2</sub> (N/mm <sup>2</sup> )	R <sub>m</sub> (N/mm <sup>2</sup> )	A <sub>5</sub> (%)	Impact Energy (J) ISO-V			T (°C)	-20°C	-40°C	-60°C	AW	115-140	275-315	25-35				562-633																	
Heat Treatment	R <sub>p0,2</sub> (N/mm <sup>2</sup> )	R <sub>m</sub> (N/mm <sup>2</sup> )					A <sub>5</sub> (%)	Impact Energy (J) ISO-V			T (°C)																											
			-20°C	-40°C	-60°C																																	
AW	115-140	275-315	25-35				562-633																															
AW: as welded																																						
<b>WELDING PARAMETERS / PACKING</b>	<table border="1"> <thead> <tr> <th colspan="3">Welding Parameters</th> <th colspan="3">Packing</th> </tr> <tr> <th>D (mm)</th> <th>Voltage (V)</th> <th>Current (A) DC+</th> <th>spool type</th> <th>kg / spool/ drum</th> <th>kg / pallet</th> </tr> </thead> <tbody> <tr> <td>0.8</td> <td>14-23</td> <td>60-160</td> <td>D-200 / KD-300 / drum</td> <td>2 / 7 / 80</td> <td>400 / 504 / 320</td> </tr> <tr> <td>1.0</td> <td>15-26</td> <td>90-210</td> <td>D-200 / KD-300 / drum</td> <td>2 / 7 / 80</td> <td>400 / 504 / 320</td> </tr> <tr> <td>1.2</td> <td>20-29</td> <td>140-260</td> <td>D-200 / KD-300 / drum</td> <td>2 / 7 / 80</td> <td>400 / 504 / 320</td> </tr> <tr> <td>1.6</td> <td>25-30</td> <td>190-350</td> <td>KD-300 / drum</td> <td>7 / 80</td> <td>504 / 320</td> </tr> </tbody> </table>		Welding Parameters			Packing			D (mm)	Voltage (V)	Current (A) DC+	spool type	kg / spool/ drum	kg / pallet	0.8	14-23	60-160	D-200 / KD-300 / drum	2 / 7 / 80	400 / 504 / 320	1.0	15-26	90-210	D-200 / KD-300 / drum	2 / 7 / 80	400 / 504 / 320	1.2	20-29	140-260	D-200 / KD-300 / drum	2 / 7 / 80	400 / 504 / 320	1.6	25-30	190-350	KD-300 / drum	7 / 80	504 / 320
Welding Parameters			Packing																																			
D (mm)	Voltage (V)	Current (A) DC+	spool type	kg / spool/ drum	kg / pallet																																	
0.8	14-23	60-160	D-200 / KD-300 / drum	2 / 7 / 80	400 / 504 / 320																																	
1.0	15-26	90-210	D-200 / KD-300 / drum	2 / 7 / 80	400 / 504 / 320																																	
1.2	20-29	140-260	D-200 / KD-300 / drum	2 / 7 / 80	400 / 504 / 320																																	
1.6	25-30	190-350	KD-300 / drum	7 / 80	504 / 320																																	
<b>REDRYING TEMPERATURE</b>	not required																																					
<b>GAS ACC. EN ISO 14175:</b>	I1, I3																																					