

Alu-Flux

CATEGORY	Brazing	
TYPE	Flux for aluminium brazing	
CLASSIFICATION	EN ISO	1045: FL 10
	DIN	8511: F-LH1
SUITABLE FOR	Brazing for aluminium and aluminium alloys with a working range from 450 to 620 degrees celsius. Usualy combined with AISi12 or AISi5 filler metal.	
APPROVALS	CE approved	