

## Super-Flux

CATEGORY	Brazing	
TYPE	Excellent low temperature flux for use with silver brazing alloys	
PROPERTIES	Superflux removes oxides and impurities from the surface during the heating process to obtain perfect bonding of the brazing filler metal. Superflux also reduces the surface tension and improves capillarity. After brazing flux residues can easily be removed mechanically or with a caustic soda solution.	
CLASSIFICATION	AWS	FB 3K
	EN ISO	1045: FH 21
	DIN	8511: F-SH1
SUITABLE FOR	Flux for silver brazing with a melting range from 450 till 850 degrees Celsius, for copper, brass, steel and stainless steel.	
APPROVALS	CE approved	