

SP 95/5 (NiAl)

CATEGORY Metal spray wires

TYPE SP 95/5 is a Nickel-Aluminum based alloy for use as a bonding layer with the thermal spray process

APPLICATIONS New coatings on machine parts and shafts to increase life, rebuilding wornout parts etc. Layer thickness: approximately 0.1- 0.15 mm.

PROPERTIES This alloy offers the highest bonding properties available for both the Flame spray process as the Arc Spray process. The wire has a high polished and clean surface to assure the best feeding and thermal spray properties. Sprayed layers of this material are-resistant to variation in high temperatures and are used as a buffer layer for all other spraying alloys. Hardness, coating macro: approximately HRc 22. Maximum working temperature: approximately 850° C

CLASSIFICATION DIN: W.Nr. 2.4155

SUITABLE FOR Shafts, clutches, gliding surfaces, valves, bond coatings etc.

WELDING POSITIONS:



PURE CAST ANALYSIS %

Al	Ni
5	95

MECHANICAL PROPERTIES

Heat Treatment	R _{p0,2} (N/mm ²)	R _m (N/mm ²)	A ₅ (%)	Impact Energy (J) ISO-V			Hardness HRc
				-20°C	-40°C	-60°C	
							22

WELDING PARAMETERS / PACKING

Process Parameters			Packing	
D (mm)	Voltage (V)	Current (A)	spool type	kg / spool
1.6	28	100-250	K-300 / D-300	13-15
3.17	30	150-350	K-415 / H-420	25-27

REDRYING TEMPERATURE not required