


## 308 L Tig

<b>CATEGORY</b>	GMAW-GTAW Solid wires																																			
<b>TYPE</b>	Stainless steel Tig filler metal for welding CrNi 18/10 types.																																			
<b>APPLICATIONS</b>	Boilers, agriculture, liquid storage tanks, food machinery, furniture.																																			
<b>PROPERTIES</b>	308L has good general corrosion resistance. The alloy has a low carbon content, making it particularly recommended where there is a risk of intergranular corrosion.																																			
<b>CLASSIFICATION</b>	AWS	A 5.9: ER 308L																																		
	EN ISO	14343-A: W 19 9 L																																		
	DIN: W.Nr.	1.4316																																		
	DIN	8556: SG X2CrNi 19 9																																		
<b>SUITABLE FOR</b>	W.Nr:	1.4306, 1.4301, 1.4541, 1.4550, 1.4311, 1.4546, 1.4312, 1.4300, 1.4312, 1.4371, 1.4541, 1.4543, 1.4550, 1.4452																																		
	DIN	X2CrNi 19 11 (TP), X4CrNi 18 10 (TP), X6CrNiTi 18 10 (TP), X6CrNiNb 18 10 (TP), X2CrNiN 18 10 (TP), X5CrNiNb 18 10, G-X10CrNi 18 8 (TP),																																		
	AISI	202, 302, 304L, 304, 305, 321, 347, 304 LN																																		
		ASTM A320 Grade B8C/D, 302																																		
<b>APPROVALS</b>	CE approved																																			
<b>WELDING POSITIONS:</b>																																				
<b>WELD METAL WEIGHT %</b>	<table border="1"> <thead> <tr> <th>C</th> <th>Mn</th> <th>Si</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> <th>P</th> <th>S</th> </tr> </thead> <tbody> <tr> <td>&lt;0.03</td> <td>1.0-2.5</td> <td>0.3-0.65</td> <td>19.5-22.0</td> <td>9.0-11.0</td> <td>&lt;0.75</td> <td>&lt;0.03</td> <td>&lt;0.03</td> </tr> </tbody> </table>							C	Mn	Si	Cr	Ni	Mo	P	S	<0.03	1.0-2.5	0.3-0.65	19.5-22.0	9.0-11.0	<0.75	<0.03	<0.03													
C	Mn	Si	Cr	Ni	Mo	P	S																													
<0.03	1.0-2.5	0.3-0.65	19.5-22.0	9.0-11.0	<0.75	<0.03	<0.03																													
<b>MECHANICAL PROPERTIES</b>	<table border="1"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R<sub>p0,2</sub> (N/mm<sup>2</sup>)</th> <th rowspan="2">R<sub>m</sub> (N/mm<sup>2</sup>)</th> <th rowspan="2">A<sub>5</sub> (%)</th> <th colspan="3">Impact Energy (J) ISO-V</th> <th rowspan="2">Hardness HRc / HV</th> </tr> <tr> <th>20°C</th> <th>-60°C</th> <th>-196°C</th> </tr> </thead> <tbody> <tr> <td>AW</td> <td>480</td> <td>630</td> <td>37</td> <td>170</td> <td>150</td> <td>75</td> <td></td> </tr> </tbody> </table>							Heat Treatment	R <sub>p0,2</sub> (N/mm <sup>2</sup> )	R <sub>m</sub> (N/mm <sup>2</sup> )	A <sub>5</sub> (%)	Impact Energy (J) ISO-V			Hardness HRc / HV	20°C	-60°C	-196°C	AW	480	630	37	170	150	75											
Heat Treatment	R <sub>p0,2</sub> (N/mm <sup>2</sup> )	R <sub>m</sub> (N/mm <sup>2</sup> )	A <sub>5</sub> (%)	Impact Energy (J) ISO-V			Hardness HRc / HV																													
				20°C	-60°C	-196°C																														
AW	480	630	37	170	150	75																														
AW: as welded																																				
<b>WELDING PARAMETERS / PACKING</b>	<table border="1"> <thead> <tr> <th rowspan="2">D (mm)</th> <th colspan="2">Welding Parameters</th> <th colspan="2">Packing</th> </tr> <tr> <th colspan="2">Current (A) DC-</th> <th>single</th> <th>master</th> </tr> </thead> <tbody> <tr> <td>1.6 x 1000</td> <td colspan="2">50-80</td> <td>5</td> <td>25</td> </tr> <tr> <td>2.0 x 1000</td> <td colspan="2">70-110</td> <td>5</td> <td>25</td> </tr> <tr> <td>2.4 x 1000</td> <td colspan="2">110-180</td> <td>5</td> <td>25</td> </tr> <tr> <td>3.2 x 1000</td> <td colspan="2">150-250</td> <td>5</td> <td>25</td> </tr> </tbody> </table>							D (mm)	Welding Parameters		Packing		Current (A) DC-		single	master	1.6 x 1000	50-80		5	25	2.0 x 1000	70-110		5	25	2.4 x 1000	110-180		5	25	3.2 x 1000	150-250		5	25
D (mm)	Welding Parameters		Packing																																	
	Current (A) DC-		single	master																																
1.6 x 1000	50-80		5	25																																
2.0 x 1000	70-110		5	25																																
2.4 x 1000	110-180		5	25																																
3.2 x 1000	150-250		5	25																																
<b>REDRYING TEMPERATURE</b>	not required																																			
<b>GAS ACC. EN ISO 14175:</b>	I1																																			