


CATEGORY	FCAW Flux-Cored																												
TYPE	High basic flux-cored wire for M21 shielding gas. (Typ CrMo1V, 1.7745)																												
APPLICATIONS	Foundries, production welding																												
PROPERTIES	CEWELD® AA BCrMo1V is a basic cored wire with Excellent weld puddle manipulation. Low spatter loss, easy slag removal. Extremely crack resistant. Suitable for economic welding of CrMoV-steels up to 550 °C. Due to the seamless production process the hydrogen content is below 3ml/100g weld metal even after long storage in unconditioned condition.																												
CLASSIFICATION	AWS	A 5.29: E80T5-GM2M H4 A 5.36: E80T5-M21PY-G-H4																											
	EN ISO	17634-A: T Z B M 4 H5																											
	F-nr	6																											
	FM	4																											
	W.Nr.	-1.7745																											
SUITABLE FOR	Typ 1Cr0.5Mo,V ISO 15608: -5,1 1.7335, 1.7262, 1.7728, 1.7218, 1.7225, 1.7258, 1.7354, 1.7357, 1.7745, 1.7706, 1.7733 13CrMo4-5, 15CrMo5, 15 CrMoV 5 10, 16CrMoV4, 25CrMo4, 42CrMo4, 24CrMo5, G22CrMo5-4, G17CrMo5-5, 24CrMoV5-5, G17CrMoV5-10 ASTM A 182 Gr. F12; A 193 Gr. B7; A 213 Gr. T12; A 217 Gr. WC6; A 234 Gr. WP11; A335 Gr. P11, P12; A 336 Gr. F11, F12; A 426 Gr. CP12																												
APPROVALS	No Approvals Found																												
WELDING POSITIONS:																													
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	<table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>P</th> <th>S</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> <th>V</th> </tr> </thead> <tbody> <tr> <td>0.1</td> <td>0.3</td> <td>0.9</td> <td>0.15</td> <td>0.015</td> <td>1.2</td> <td>0.3</td> <td>1.1</td> <td>0.25</td> </tr> </tbody> </table>					C	Si	Mn	P	S	Cr	Ni	Mo	V	0.1	0.3	0.9	0.15	0.015	1.2	0.3	1.1	0.25						
C	Si	Mn	P	S	Cr	Ni	Mo	V																					
0.1	0.3	0.9	0.15	0.015	1.2	0.3	1.1	0.25																					
ALL WELD MECHANICAL PROPERTIES	<table border="1"> <thead> <tr> <th>Heat Treatment</th> <th>R_{p0,2} (MPa)</th> <th>R_m (MPa)</th> <th>A₅ (%)</th> <th>Impact Energy (J) ISO-V</th> </tr> </thead> <tbody> <tr> <td>690°C±15°C /3h</td> <td>500</td> <td>620</td> <td>20</td> <td>70</td> </tr> </tbody> </table>					Heat Treatment	R _{p0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V	690°C±15°C /3h	500	620	20	70														
Heat Treatment	R _{p0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V																									
690°C±15°C /3h	500	620	20	70																									
WELDING PARAMETERS / PACKING	<table border="1"> <thead> <tr> <th>WELDING PARAMETERS</th> <th>WELDING PARAMETERS</th> <th>WELDING PARAMETERS</th> <th>PACKING</th> <th>PACKING</th> <th>PACKING</th> </tr> <tr> <th>D (MM)</th> <th>VOLTAGE (V)</th> <th>CURRENT (A)</th> <th>SPOOL TYPE</th> <th>KG / SPOOL</th> <th>KG / PALLET</th> </tr> </thead> <tbody> <tr> <td>1.2</td> <td>22-30</td> <td>160-280</td> <td>D-200 / BS-300/B300 / DRUM</td> <td>5 / 15 / 16 / 300</td> <td>1000 / 1080 / 1024 / 600</td> </tr> <tr> <td>1.6</td> <td>23-32</td> <td>190-350</td> <td>D-200 / BS-300/B300 / DRUM</td> <td>5 / 15 / 16 / 300</td> <td>1000 / 1080 / 1024 / 600</td> </tr> </tbody> </table>					WELDING PARAMETERS	WELDING PARAMETERS	WELDING PARAMETERS	PACKING	PACKING	PACKING	D (MM)	VOLTAGE (V)	CURRENT (A)	SPOOL TYPE	KG / SPOOL	KG / PALLET	1.2	22-30	160-280	D-200 / BS-300/B300 / DRUM	5 / 15 / 16 / 300	1000 / 1080 / 1024 / 600	1.6	23-32	190-350	D-200 / BS-300/B300 / DRUM	5 / 15 / 16 / 300	1000 / 1080 / 1024 / 600
WELDING PARAMETERS	WELDING PARAMETERS	WELDING PARAMETERS	PACKING	PACKING	PACKING																								
D (MM)	VOLTAGE (V)	CURRENT (A)	SPOOL TYPE	KG / SPOOL	KG / PALLET																								
1.2	22-30	160-280	D-200 / BS-300/B300 / DRUM	5 / 15 / 16 / 300	1000 / 1080 / 1024 / 600																								
1.6	23-32	190-350	D-200 / BS-300/B300 / DRUM	5 / 15 / 16 / 300	1000 / 1080 / 1024 / 600																								
REDRYING TEMPERATURE	Not required																												
GAS ACCORDING EN 14175	M21																												