


CATEGORY	GTAW Solid wires																															
TYPE	Copper coated welding wire for welding creep resistant ferritic steels.																															
APPLICATIONS	Is a Filler metal for high temperature creep resistant 1.25%Cr 0.5%Mo ferritic steel. These steels are used for creep resisting applications up to ~550 °C. Typical applications in power generation plant include steam piping, turbines and boilers; the alloy also finds applications in the chemical and petro-chemical industries.																															
PROPERTIES	The CEWELD® ER 80S-B2 Tig has low levels of tramp elements (e.g. Sn, As, Sb and P) providing a low Bruscato Factor(X< 10 ppm)for temper embrittlement resistant applications.																															
CLASSIFICATION	AWS	A 5.28: ER 80S-B2																														
	EN ISO	21952-B: W 1CM																														
	F-nr	6																														
	FM	3																														
SUITABLE FOR	For matching 1.25%Cr 0.5%Mo creep resisting ferritic steels. 13CrMo4-5, 16CrMo4-4, GS-17CrMo5-5 ASTM: A182 grades F11/F12, A199/A200 T11, A217 grades WC6/WC11, A234 grades WP11/WP12, A335 grades P11/P12, A387 grades 11/12																															
APPROVALS	CE																															
WELDING POSITIONS:																																
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	<table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>Cr</th> <th>Mo</th> </tr> </thead> <tbody> <tr> <td>0.09</td> <td>0.6</td> <td>0.6</td> <td>1.3</td> <td>0.5</td> </tr> </tbody> </table>			C	Si	Mn	Cr	Mo	0.09	0.6	0.6	1.3	0.5																			
C	Si	Mn	Cr	Mo																												
0.09	0.6	0.6	1.3	0.5																												
ALL WELD MECHANICAL PROPERTIES	<table border="1"> <thead> <tr> <th>Heat Treatment</th> <th>R_{p0.2} MPa</th> <th>R_m MPa</th> <th>A₅ (%)</th> <th>Impact Energy (J) ISO-V RT</th> </tr> </thead> <tbody> <tr> <td>660°C- 700°C /1h</td> <td>460</td> <td>560</td> <td>20</td> <td>55</td> </tr> </tbody> </table>			Heat Treatment	R _{p0.2} MPa	R _m MPa	A ₅ (%)	Impact Energy (J) ISO-V RT	660°C- 700°C /1h	460	560	20	55																			
Heat Treatment	R _{p0.2} MPa	R _m MPa	A ₅ (%)	Impact Energy (J) ISO-V RT																												
660°C- 700°C /1h	460	560	20	55																												
WELDING PARAMETERS / PACKING	<table border="1"> <thead> <tr> <th rowspan="2">D (MM)</th> <th>WELDING PARAMETERS</th> <th>WELDING PARAMETERS</th> <th colspan="2">PACKING (KG)</th> </tr> <tr> <th>CURRENT (A) (DC-)</th> <th></th> <th>SINGLE</th> <th>MASTER</th> </tr> </thead> <tbody> <tr> <td>1.6 X 1000</td> <td>50-80</td> <td></td> <td>5</td> <td>25</td> </tr> <tr> <td>2.0 X 1000</td> <td>70-110</td> <td></td> <td>5</td> <td>25</td> </tr> <tr> <td>2.4 X 1000</td> <td>110-180</td> <td></td> <td>5</td> <td>25</td> </tr> <tr> <td>3.2 X 1000</td> <td>150-250</td> <td></td> <td>5</td> <td>25</td> </tr> </tbody> </table>			D (MM)	WELDING PARAMETERS	WELDING PARAMETERS	PACKING (KG)		CURRENT (A) (DC-)		SINGLE	MASTER	1.6 X 1000	50-80		5	25	2.0 X 1000	70-110		5	25	2.4 X 1000	110-180		5	25	3.2 X 1000	150-250		5	25
D (MM)	WELDING PARAMETERS	WELDING PARAMETERS	PACKING (KG)																													
	CURRENT (A) (DC-)		SINGLE	MASTER																												
1.6 X 1000	50-80		5	25																												
2.0 X 1000	70-110		5	25																												
2.4 X 1000	110-180		5	25																												
3.2 X 1000	150-250		5	25																												
REDRYING TEMPERATURE	Not required																															
GAS ACCORDING EN 14175	I1																															